



1070

Extra Tile and Ceramic Adhesive Mortar



Product Code : 1070
Quality Certificates

The product conforms to the EN 12004-1 standard C1TE class.

Description: A cement-based, single component powder mortar with extra properties. Used for bonding ceramic and tiles.

Application Areas: Indoor and outdoor, horizontal and vertical surfaces, bonding small and medium size floor and wall ceramics, mosaics and similar materials with more than 3% water absorption rate.

Advantages:

- Easily applied.
- Provides longer time for working, saves time and labor.
- Enables bonded plates to be adjusted in a long time period.
- Resistant to water and frost.
- Provides high stability and does not cause sagging in vertical applications.
- Allows tiling downwards.

Preparation of the Surface: Special attention must be given that the application surface is cured. The application surface must be clear of materials which prevent bonding, such as dust, oil, paint, silicone, curing agents and detergents. The application surface must be wet and kept damp. If the water absorption of the surface is high, the product must be applied after the primer.

Preparation of the Mortar: 25 kg of Falcon Extra Tile and Ceramic Adhesive Mortar is added to approximately 6,5 - 7 liters of clean water and mixed by a mixer with low speed or with a trowel, until there are no lumps. Prepared mortar should be left to mature for 5 - 10 minutes, mixed again before use. The mortar must be used within 2.5 - 3 hours.

Application Information: A contact layer is generated by

pressing the adhesive mortar strongly onto the application surface, the layer is combed with an appropriate notched trowel. The adhesive mortar must contact at least 80% of the backside of the ceramic. Depending on the plates used and the flatness of the surface, adhesive mortar can be applied both on the backside of the ceramic and on the surface, for a double sided bonding. Combing directions must be perpendicular to each other. For better bonding, apply force with a rubber hammer.

Consumption: 3.5 - 4 kg/m²

Caution: Avoid application in temperatures below +5°C and above +35°C. Avoid application on frozen areas, on areas under risk of freezing in 24 hours or on areas open to direct sunlight or wind. Never attempt to extend the expired mortar by adding powder and water. The values mentioned above are obtained at 23±2°C and 50±5 relative humidity conditions.

Packaging: 25 kg craft bags

Shelf Life: Unopened packages can be stored in dry environments for up to 12 months, stacked maximum 10 packages on a pallet.

Health and Safety: As with all chemical products, contact with food, skin, eyes and mouth should be avoided during usage and storing. If swallowed by accident, consult a doctor. In case of contact with skin, rinse with plenty of water. Keep out of reach of children.



Technical Properties	
Appearance	: Grey colored fine powder
Powder Density	: ~1.30 kg/l
Water Mixing Rate	: 6.5 - 7 lt water / 25 kg powder
Resting Period	: 5 - 10 minutes
Pot Life	: Appr. 2 - 2.5 hours
Extended Open Time	Tensile Adhesion Strength : After min. 30 minutes ≥ 0.5 N/mm ² (EN 1346)
Application Temperature	: Between +5°C and +35°C
Tensile Adhesion Strength	: ≥ 0.5 N/mm ² 28 days (EN 1348)
Slip	: ≤ 0.5 mm (EN 1308)
Walk-on Time	: 24 hours
Service Temperature	: -20°C / +70°C

Application instructions and technical data provided for the products are obtained in line with our experience and the tests we implemented according to international standards under ambient temperatures of 23 ± 2 °C and ambient relative humidity conditions of 50% ± 5. Higher temperatures decrease the times and lower temperatures increase them.