



6000

Double Component Semi - Elastic Isolation Material



Product Code : 6000
Quality Certificates

The product conforms to the EN 1504-2 standard.

Safe to Use in drinking water systems

Description: A cement and acrylic-based, semi-elastic, two components water isolation material. Components must be mixed before application. Resistant to positive water pressure.

Application Areas: Indoor and outdoor, horizontal and vertical applications, wet areas, such as bathroom, kitchen, balcony, water tanks, swimming pools (under the coverage), groundwork isolation, isolation of deck roofs, retaining walls, isolation of concrete flower receptacle.

Advantages:

- Easily applied on horizontal and vertical surfaces with a brush, roller, trowel or spraying machine.
- Not affected by weather temperature.
- Provides seamless water isolation, without joints.
- Waterproof and partially flexible.
- Allows the concrete to breathe.
- Non-poisonous, can be used indoors.
- Generates an economical water isolation layer under ceramics and screed, due to its high bonding property and semi-elastic structure.

Preparation of the Surface: Attention must be given that the application surface is cured. The application surface must be clear of materials which prevent bonding, such as dust, oil, paint, silicone, curing agents, detergents and mold release oils. Weak parts of the concrete must be repaired, plasters that are not well adhered must be removed, the surface must be flat and sound, static cracks on the building must be repaired with High Strength Shrinkage Compensated Repair Mortar. Dynamic (moving) cracks must be repaired with Polyurethane Sealant. Irons and wedges on the surface must be removed and the holes that have water outflow must be filled with appropriate products, such as Rapid Setting Plugging Mortar. The surface must be saturated with water and must be kept moist during the application.

Preparation of the Mortar: Put Component B (5.4 kg) in a clean pot. Add Component A (20 kg) into the liquid slowly and mix preferably with a drill with low speed until there are no lumps. Do not add water. Leave the mixture to mature for 3 - 5 minutes, mix again for 30 seconds before usage. The mixture in the pot must be used within 30 minutes. In case this duration is exceeded, the mortar should not be used.

Application Information: Falcon Double Component Semi-Elastic Isolation Material is applied on the surface at least in 2 layers that are perpendicular to each other. There must be a waiting period between two applications, minimum 5 - 6 hours – maximum 24 hours, at +20°C. Second layer must be applied before the first layer is completely dry. In case the first layer is dry, the surface must be moisturized again before the application of the second layer. The surface must be protected from sunlight and prevented from drying quickly, for 3 days after the application of the second layer. After the application of the first layer, the corners have to be beveled before the application of the second layer. It is recommended to use a mesh between the coats. It gains mechanical strength in 3 days, becomes waterproof in 7 days. It gains its final strength in 14 days. It has to be protected against any impact until it is over-coated.

Consumption: 1 – 1.5 kg/m² is applied on each layer, in 1 mm thickness. It is recommended that at least 2 layers are applied (2 - 3 kg/m²). On areas where stronger protection is required, the consumption may increase up to 3 - 4 kg/m².

Caution: Avoid application in temperatures below +5°C and above +35°C. Avoid application on frozen areas, on areas under risk of freezing in 24 hours or on areas open to direct sunlight or wind. Do not add water to the mixture. Always add powder component into the liquid component. During the application, wet film thickness should not exceed 2 mm per coat. The values mentioned above are obtained at 23±2°C and 50±5 relative humidity conditions.

Packaging: Component A: 20 kg craft bags
Component B: 5.4 kg plastic drums

Shelf Life: Unopened packages can be stored in dry environments for 12 months and stacked 10 packages on a pallet. Shake the liquid component before use and protect it against frost.

Health and Safety: As with all chemical products, contact with food, skin, eyes and mouth should be avoided during usage and storing. If swallowed by accident, consult a doctor. In case of contact with skin, rinse with plenty of water. Keep out of reach of children.



Technical Properties

Appearance	: Component A: Grey colored fine powder Component B: White colored liquid
Density	: Component A: ~1.40 kg/lt Component B: ~1.01 kg/lt
Mixture Rate	: 5.4 kg liquid / 20 kg powder
Resting Period	: 3 - 5 minutes
Flexibility	: Medium
Application Temperature	: Between +5°C and +35°C
Resistance to Pressurized Water	: 2 bar positive (DIN 1048)
Capillary Absorption and Permeability to Water	: $w < 0.1 \text{ kg}/(\text{m}^2 \cdot \text{h}^{0.5})$ (EN 1062-3)
Time to Use	: Mechanical Strength : 3 days Waterproofness : 7 days
Time to Cover	: 3 days
Service Temperature	: -10°C / +70°C

Application instructions and technical data provided for the products are obtained in line with our experience and the tests we implemented according to international standards under ambient temperatures of 23 ± 2 °C and ambient relative humidity conditions of 50%±5. Higher temperatures decrease the times and lower temperatures increase them.